



# ECOPART 84 S

## Release agent for cold-curing processes

### Product Properties

---

ECOPART 84 S is a release agent for cold-curing processes. The blue coloring visualizes the areas on the pattern, where release agent either still exists or just has been applied. This enables exact application in spots where the release agent is missing. ECOPART 84 S is suitable for furan and phenol resins, ASKOSET and AVENOL NB. The viscosity setting is such that both brush-on and spray-on processing are possible. Styrofoam patterns do not react with ECOPART 84 S after short-term exposure.

### Analytical values

---

- Modified waxes in highly volatile hydrocarbons
- State: Liquid to paste
- Color: blue
- Odor: hydrocarbons
- Solids content: 12.0 – 14.0%
- Flash point DIN 51755: approx. 12°C

### Storage & Handling

---

- Product Storage Conditions: 24 months under normal conditions
- Shake or stir before use
- Keep away from sources of ignition
- NO SMOKING
- Ensure good room ventilation

#### Packaging

- Canister: 8 kg
- Steel can: 16 kg
- Drum: 130 kg
- Labelling: Please refer to the Safety Data Sheet

### Complimentary Products

---

ASKURAN, BERANOL, ASKOSET, AVENOL NB