



ECOPART 80 S

Release agent for cold-curing processes

Product Properties

ECOPART 80 S is a release agent for cold-curing processes. The blue coloring visualizes the areas on the pattern, where release agent either still exists or just has been applied. This enables exact application in spots where the release agent is missing. ECOPART 80 S is suitable for furan and phenol resins, ASKOSET and AVENOL NB. The viscosity setting is such that both brush-on and spray-on processing are possible. The product is free of chloro- and chlorofluorohydrocarbons. Styrofoam patterns do not react with ECOPART 80 S after short-term exposure.

Analytical values

- Modified waxes in highly volatile hydrocarbons
- State: Liquid
- Color: Blue
- Odor: hydrocarbons
- Solids content: 3.3 – 4.3 %
- Flash point DIN 51755: approx. -12°C

Storage & Handling

- Product Storage Conditions: 24 months under normal condition
- Shake or stir before use
- Keep away from sources of ignition
- NO SMOKING
- Ensure good room ventilation
- Labelling: Please refer to the Safety Data Sheet

Packaging

- Canister: 8 kg
- Steel can: 16 kg
- Drum: 145 kg
- Container: 250 kg

Complimentary Products

ASKURAN, BERANOL, ASKOSET, AVENOL NB